



ESGARD

EQUIPMENT KOTE BRUSHABLE BLACK

DESCRIPTION	Equipment Kote (Brushable Black) is a hard drying thin film preservative for long term indoor and outdoor storage protection of properly prepared or machined surfaces where it is not desirable to paint.
FIELD OF APPLICATION	Indoor/outdoor parts storage, automotive undercoating, protection of overseas shipments

TECHNICAL DATA

TYPE	Firm, rust inhibitive modified wax
VOLUME SOLIDS	33%
V.O.C.	4.3 lb/gal (516 g/l)
DENSITY	8.22 lbs/gal (.99 kg/l)
COVERAGE (Theoretical)	529sq ft/gal at 1 mil dry (3.0 mils wet) 13.0 sq m/l at 25 microns dry (75 microns wet)
RECOMMENDED DRY FILM THICKNESS	4.0 – 6.0 mils
DRY TIME (HOURS) @ 5 MILS DFT 65% R.H.	To Touch 1 – 2 Hours To Handle 3 – 6 Hours Recoat 3 – 6 Hours

SURFACE PREPARATION Thoroughly clean any oil or grease contaminated areas with Esgard Surface Conditioner or a detergent wash followed by a fresh water rinse and allow drying in accordance with SSPC-SP1-82.

Hand clean to SSPC-SP2-82 wire brush surface to remove all dirt, rust, and other surface contaminants or abrasive blast to SSPC-SP6-82 commercial surface or better with a 1.5-2.0 mil (37-50 micron) anchor profile.

Manufacturers of Quality Protective Coatings
Esgard, Inc. . 515 Debonnaire Road Scott, Louisiana 70583 U.S.A.
(337)234-6327 Fax (337) 234-0113 1-800-888-2511

www.esgardcoatings.com



EQUIPMENT KOTE BRUSHABLE BLACK PAGE 2

APPLICATION	<p><u>Mix</u> – Power mix or hand mix until mixture is uniform.</p> <p><u>Thin</u> – Thinning not normally required.</p> <p><u>Spray</u> - Use suitable conventional or airless spray equipment. The following has been found adequate:</p> <p><u>Conventional</u> - Pressure pot should have an oil/water trap, double regulators, and minimum 3/8" I.D. fluid and air hose. Gun should be a DeVilbiss with a D tip and #64 air cap, or Binks with a #68 set up.</p> <p><u>Airless</u> - Use Graco Bulldog 30:1 or equal with Teflon packing with minimum 3/8" I.D. fluid hose. Gun should have a fluid tip size .019 - .025. Fluid tip pressure should be 2300 - 2600 p.s.i.</p> <p><u>Brush</u> – Apply Equipment Kote with a clean pure china bristle paint brush.</p> <p><u>Roll</u> – Not recommended</p>						
CLEAN UP	Esgard Thinner 106. For personal cleanup, use soap and water.						
ORDERING INFORMATION							
CONTACT #	1-800-888-2511						
SHIPPING WEIGHT	<table><thead><tr><th></th><th><u>5 GAL</u></th><th><u>55GAL</u></th></tr></thead><tbody><tr><td>Equipment Kote Brushable Black Thinner 106</td><td>42.6 lb (21.0 kg) 8.5 lb (3.9 kg)</td><td>511.0 lb (232 kg) 42.0 lb (19.0 kg)</td></tr></tbody></table>		<u>5 GAL</u>	<u>55GAL</u>	Equipment Kote Brushable Black Thinner 106	42.6 lb (21.0 kg) 8.5 lb (3.9 kg)	511.0 lb (232 kg) 42.0 lb (19.0 kg)
	<u>5 GAL</u>	<u>55GAL</u>					
Equipment Kote Brushable Black Thinner 106	42.6 lb (21.0 kg) 8.5 lb (3.9 kg)	511.0 lb (232 kg) 42.0 lb (19.0 kg)					
FLASH POINT	Equipment Kote Brushable Black Thinner 106 105°F (40°C) 105°F (41°C)						
COLORS	Black.						
SHELF LIFE	Eighteen (18) months from date of shipment.						
CAUTION	FOR INDUSTRIAL USE ONLY! FLAMMABLE! Contains petroleum distillates. DO NOT USE NEAR HEAT, SPARKS, OR FLAMES. Close container after use.						
SAFETY	Refer to Material Safety Data Sheet supplied with each order.						
FIRST AID	Refer to Material Safety Data Sheet supplied with each order.						

Manufacturers of Quality Protective Coatings
Esgard, Inc. . 515 Debonnaire Road Scott, Louisiana 70583 U.S.A.
(337)234-6327 Fax (337) 234-0113 1-800-888-2511

www.esgardcoatings.com